

THE EFFECT OF MATERIAL NON-LINEARITY ON THE PREDICTED PERFORMANCE OF ROAD PAVEMENT

MOHAMAD YUSRI BIN AMAN

KOLEJ UNIVERSITI TEKNOLOGI TUN HUSSEIN ONN

CN/700/2

PERPUSTAKAAN KUI TTHO



3 0000 00117418 8

BORANG PENGESAHAN STATUS TESIS ♦

JUDUL : THE EFFECT OF MATERIAL NON-LINEARITY ON THE
PREDICTED PERFORMANCE OF ROAD PAVEMENT

SESI PENGAJIAN : 2002/2003

Saya MOHAMAD YUSRI BIN AMAN
(HURUF BESAR)

mengaku membenarkan tesis (PSM/Sarjana/Doktor Falsafah)* ini disimpan di Perpustakaan Universiti Teknologi Malaysia dengan syarat-syarat kegunaan seperti berikut:

1. Tesis adalah hakmilik Kolej Universiti Teknologi Tun Hussein Onn.
2. Perpustakaan Universiti Teknologi Malaysia dibenarkan membuat salinan untuk tujuan pengajian sahaja.
3. Perpustakaan dibenarkan membuat salinan tesis ini sebagai bahan pertukaran di antara institusi pengajian tinggi.
4. ** Sila tandakan (✓).

☐

SULIT

(Mengandungi maklumat yang berdarjah keselamatan atau kepentingan Malaysia seperti yang termaktub di dalam AKTA RAHSIA RASMI 1972)

☐

TERHAD

(Mengandungi maklumat TERHAD yang telah ditentukan oleh organisasi/badan di mana penyelidikan dijalankan)

☒

TIDAK TERHAD

Disahkan oleh


(TANDATANGAN PENULIS)

Alamat Tetap: No 8. JALAN BAYAS
TAMAN SOGA, 83000 BATU PAHAT


(TANDATANGAN PENYELIA)

DR. KEMAS AHMAD ZAMHARI

Nama Penyelia

Tarikh: 08 APRIL 2004

Tarikh: 09 APRIL 2004

CATATAN: * Potong yang tidak berkenaan.

**Jika tesis ini SULIT atau TERHAD, sila lampirkan surat daripada pihak berkuasa/organisasi berkenaan dengan menyatakan sekali sebab dan tempoh tesis ini perlu dikelaskan sebagai SULIT atau TERHAD.

♦ Tesis dimaksudkan sebagai tesis bagi Ijazah Doktor Falsafah dan Sarjana secara Penyelidikan, atau disertasi bagi pengajian secara kerja kursus dan penyelidikan, atau Laporan Projek Sarjana Muda (PSM)

“I have read this proposal and it is my professional view that it has fulfil the requirement of Master Degree in Civil Engineering”

Signature : 

Supervisor's name : Dr. Kemas Ahmad Zamhari.

Date : 09th April 2004

**THE EFFECT OF MATERIAL NON-LINEARITY ON THE PREDICTED
PERFORMANCE OF ROAD PAVEMENT**

MOHAMAD YUSRI BIN AMAN


This project report is submitted for fulfil
a part from award condition for Master Degree of Civil Engineering

Engineering Faculty
University Collage of Technology Tun Hussein Onn

NOVEMBER, 2003

DECLARATION

“I admit that this report is written on my own effort except for the quotation
and summary which I have stated and source”

Singature : 

Name : Mohamad Yusri Bin Aman

Date : 08th April 2004

ACKNOWLEDGEMENT

In the name of Allah SWT the Compassionate and Most Merciful. I would like to forward my most thanks to my supervisor, Dr. Kemas Ahmad Zamhari, for the entire guidance, advise and suggestions in preparing this project paper, to Mr. Adnan Bin Zainorabidin and Mr. Ahmad Kamal Ariffin. My appreciation also goes to Mr. Ir. Othman Bin Ja'afar, Mr. Khairulanuar Bin Mohd Nayan and Mr. Mohd. Ashari Bin Jani from engineering geotechnical laboratory, Universiti Kebangsaan Malaysia, Bangi in assisting and teaching on the use, handling and preparing the equipment for this project.

My gratitude and sincere thanks also goes to Mr. Mohd Baharudin, my friends in participating by offering their help in making this project paper possible and who was brought me to be critical thinking.

Last but not least, I also wish to express my appreciation to my beloved parents, all friend and those who have contributed in giving me the moral support and being with me for these long years together. May the blessing of Allah SWT be with them

For those I have over looked - Thank You Very Much.

DEDICATION

*I would like to forward my appreciation to my father and mother,
to my family who have been giving me
the moral support,....*

To my wife Norizah Bte Mesdi,

thank you for sacrificing and the commitment support,....

*To my son Muhammad Afiq Amsyar and my daughter Nor Balqis MayangSari,
you are my love and follow the way which have been given,....*

and

Thank you to those who brought me to be critical thinking.

ABSTRACT

The purpose of this study is to determine the effect of non-linearity of unbound granular material as base course on the road pavement. This study focused in the determination of the effect of density and level of stress on resilient modulus at granular base material under repeated loading. The granular material was compacted at optimum moisture content of the 90 %, 95 % and 100 % of maximum dry density. The stress application assign to the stress situation caused by wheel loading affected at the base, upper subbase and lower subbase layer pavement. From the test result, the graph was plotted by regression analysis and the model fitted base on Brown and Pell, 1976, as $M_r = k_1 (\sigma/\sigma_0)^{k_2}$. The result obtained was analysed by Analysis of Variant (ANOVA) using t-test to determine the effect of resilient modulus on density and level of stress. The resilient modulus increases as the level of stress and density increase, which means that the resilient modulus of unbound granular material is stress dependent and the relationship is non-linear. The effect of non-linear unbound granular material on the road pavement is determined by MICH-PAVE software. The flexible pavement was analysed based on Manual of Pavement Design (JKR) which the standard and construction layer thickness was taken. The analyses consist of the maximum horizontal tensile and the average compressive strains in asphalt layer and compressive strain at the top subgrade. These strains are related to the fatigue life and rut depth of asphalt pavement. The resilient modulus increases with the increase in density. Everything being equal pavement with unbound layer with lower may have a higher horizontal or radial strain at the bottom of asphalt, and therefore will have shorter fatigue life. The lower density at the unbound layer tends to increase the average compressive strain within the asphalt layer and compressive strain at the top of subgrade, which may cause at the increment rate total plastic deformation at the pavement.

ABSTRAK

Kajian ini adalah bertujuan untuk mendapatkan kesan tidak linear bahan batu baur sebagai lapisan tapak didalam turapan jalan raya. Kajian ini adalah untuk mendapatkan kesan dari ketumpatan dan peringkat tekanan (stress) keatas resilient modulus pada lapisan tapak apabila beban ulangan dikenakan. Bahan batu baur dipadatkan pada kandungan lembapan optima iaitu 90 %, 95 % dan 100 % ketumpatan kering maksima. Tekanan akan dikenakan sebagai mengandaikan keadaan di jalan raya yang disebabkan oleh beban tayar kenderaan pada lapisan tapak, sub tapak dan bahagian bawah sub tapak lapisan turapan. Dari ujikaji ini, graf akan diplotkan dengan menggunakan analisis regression dan model dibangunkan berdasarkan Brown dan Pell, 1976, iaitu $M_r = k_1 (\theta/\theta_0)^{k_2}$. Analisis of Variant (ANOVA) menggunakan t-test digunakan untuk mendapatkan kesan resilient modulus keatas ketumpatan dan peringkat tekanan(stress). Nilai resilient modulus akan meningkat apabila peringkat tekanan (stress) dan density meningkat, ini bermakna nilai resilient modulus untuk batu baur adalah bergantung kepada beban yang dikenakan dan pertaliannya adalah tidak linear. Kesan ketidak linearan batu baur keatas lapisan turapan diperolehi dengan menggunakan perisian MICH-PAVE. Turapan lentur dianalisa berdasarkan kepada Manual Pavement Design (JKR) dimana ketebalan lapisan pembinaan yang standard digunakan. Analisa ini meliputi kesan mendatar maksima (maximum horizontal tensile) dan purata mampatan keterikan (average compressive strains) didalam lapisan asphalt dan keterikan mampatan (compressive strain) keatas lapisan atas sub tapak. Keterikan ini mempunyai perkaitan jangka hayat dan kesan ke atas lapisan turapan. Nilai resilient modulus meningkat dengan meningkatnya peringkat keterikan. Keadaan ini memberikan kesan keatas keterikan mendatar dan pugak didalam lapisan asphalt. Peringkat mampatan yang rendah akan memberikan kesan keterikan yang tinggi dan menyebabkan jangka hayat turapan jalan akan menjadi lebih singkat.

II	LITERATURE REVIEW	5
2.1	Introduction	5
2.2	The Principles of Pavement Design	5
2.2.1	Flexible Pavement	6
2.2.2	Rigid Pavement	6
2.3	Granular Material as Base Course	7
2.4	Characteristics of Unbound Granular Material	8
2.5	Factor Affecting Resilient Response	9
2.5.1	Effect of Stress	9
2.5.2	Effect of Density	10
2.5.3	Effect of Grading	11
2.5.4	Effect of Moisture Content	11
2.5.5	Effect of Number of Load Applications	12
2.6	Resilient Modulus Models	13
III	METHODOLOGY	16
3.1	Introduction	16
3.2	Experiment Design	16
3.2.1	Three levels of Stress	17
3.2.2	Three levels of Density	19
3.3	Material	20
3.3.1	Particle Size Distribution	20
3.3.2	Dry Density- Moisture Relationship	21
3.3.3	Compaction of The Sample Specimen	21
3.3.4	The Number of Blow/layer	22
3.3.5	Specimen Preparation	24

3.4	Equipment	26
3.4.1	Mould Compaction	26
3.4.2	The Universal Testing Machine	26
3.5	Repeated Triaxial Testing Method	28
3.6	Analysis	30
3.6.1	Physical State Condition	30
3.7	Using the MICH-PAVE Computer Program	30
IV	RESULT AND ANALYSIS	32
4.1	Introduction	32
4.2	Gradation Limits	32
4.3	Compaction Test	34
4.4	The Density of Test Specimens	35
4.5	The Repeated Triaxial Load Test	36
4.6	The Non-Linearity of Resilient modulus	39
4.7	The Effect of Density	41
4.8	The Effect Level of Stress	42
4.9	The Effect of Non-Linearity on The Road Pavement	44
V	CONCLUSION AND SUGGESTION	47
5.1	Conclusion	47
5.2	Suggested For Further Research	49
	REFERENCES	50
	APPENDICES	53

LIST OF FIGURES

FIGURE NO	DISCRIPTIONS	PAGE
2.0	Stress in an unbound Granular Material	8
3.1	Stress applied on a triaxial test	17
3.2	To determine the number of blow/layer by trial and error	22
3.3	The preparation of specimen before compaction works	23
3.4	The compaction works for granular material with 4.5 kg rammer	24
3.5	Using the hydraulic jack to take out the sample from mould	25
3.6	Preparing the membrane stretcher during the mould removal	25
3.7	The mould compaction with cap and base plate	26
3.8	The Universal Testing Machine (UTM 25)	27
3.9	The specimen in the triaxial cell	29
3.10	Repeated load triaxial using Universal Testing Machine	29
4.1	The particle size distribution comply with JKR Specification	33
4.2	The Dry density and moisture content relationship	35
4.3	The resilient modulus values for each stress of level	40
4.4	Resilient modulus for 90 % maximum dry density	40
4.5	Resilient modulus for 95 % maximum dry density	41
4.6	Resilient modulus for 100 % maximum dry density	41
4.7	The effect of density and stress of level on granular material	43

LIST OF TABLE

TABLE NO	TITLE	PAGE
2.0	The elastic parameter base on Manual Pavement Design (JKR) 1985).	15
3.1	The stress level with contact stress (P) of 550 kPa.	18
3.2	The stress level on pavement layers (Stress factor).	18
3.3	The level of stress was applied on repeated triaxial load test.	18
3.4	The degrees of compaction at optimum moisture content.	19
3.5	Gradation limits of crushed aggregate for road base.	20
4.1	The gradation limit for road base aggregate base on JKR Specification.	33
4.2	The result of compaction test according B.S 1377:1990.	34
4.3	The values of dry density obtained at optimum moisture content.	35
4.4	The resilient modulus at 90 % maximum dry density for sample I.	36
4.5	The resilient modulus at 90 % maximum dry density for sample II.	36
4.6	The resilient modulus at 95 % maximum dry density for sample III.	37

4.7	The resilient modulus at 95 % maximum dry density for sample IV.	37
4.8	The resilient modulus at 100 % maximum dry density for sample V.	38
4.9	The resilient modulus at 100 % maximum dry density for sample VI.	38
4.10	The value of resilient modulus from the triaxial load test	39
4.11	The effect of density o the stress of level	42
4.12	Result of the t-test for effect of stress state	43
4.13	The achieved degrees of compaction, moisture content and the K values	44
4.14	The result from MICH-PAVE program	45
4.15	The comparison result by JKR and MICH-PAVE program	46

SYMBOLS AND ABBREVIATIONS

M_r	Resilient modulus
E	Elastic Modulus (kg/cm^2)
ν	Resilient Poisson's ratio
σ_1	Axial stress (kPa)
σ_2	Radial stress (kPa)
σ_3	Confining stress (kPa)
σ_c	Deviator or cyclic stress
$\epsilon_{ax, res}$	Resilient axial strain
$\epsilon_{rad, res}$	Resilient radial strain
θ	Sum of principal stresses (kPa)
θ_0	reference value (1 kPa)
k_1, k_2	regression coefficients

LIST OF APPENDICES

APPENDIX NO	TITLE	PAGE
1.	Repeated Triaxial Load Test Results	53
2.	Analysis of Variance Results	241
3.	MICH-PAVE Program Results	264

CHAPTER I

INTRODUCTION

1.1 Introduction

Pavement is the structure which separates the tires of vehicles from the underlying foundation material. Pavement is normally consist of multilayer construction with relatively weak materials below and progressively stronger ones above. Such an arrangement leads to the economic use of available material.

Road pavements in Malaysia have traditionally been classified as flexible pavement and rigid pavement. The flexible pavement usually consists of three main layers, the bituminous surfacing, the base or road base and the sub base, and for the rigid pavement consists of two layers, concrete slab and the subbase.

The surfacing is generally divided into the wearing course and the binder course laid separately. The base and sub base may also be laid in composite form using different materials designated the upper and lower base or sub base. Where the soil is considered very weak, a capping layer may also be introduced between the sub base and the soil foundation and generally referred to as the sub grade and the surface of the sub grade is termed the formation level.

The rigid pavement is cement concrete pavements and normally consist of two layers only, the concrete slab and the subbase. The slab may be laid in composite form using different aggregates in the upper and lower layers. Concrete pavements may be reinforced with steel mesh or they may be unreinforced. The function of the reinforcement is to hold any cracks which form from opening and is intended to

distribute cracks uniformly along the length of the pavement, the intention being to prevent isolated wide cracks.

1.2 Pavement Issues

The incremental of traffic volume will create the congestion of the roads and will deteriorate the pavements and reduces its lifetime. The increase of load and the number of load repetitions on the pavement may induce permanent deformation and fatigue cracking on the bounded layer in pavement layer structure. The maintenance and reconstruction may involve a high investment cost.

1.3 Pavement Design

The road pavement design related to traffic, design life and pavement thickness for various forms of pavement. Methods of pavement design can be classified as *empirical and mechanistic-empirical methods*.

The *empirical method* is used without a strength test dates back to the development of the Public Roads soil classification system in which subgrade was classified as uniform from A1 to A7 and nonuniform from B1 to B3. The system was later modified by the Highway Research Board in 1945 in which soils were grouped from A1 to A7 and was added to differentiate the soil within each group. The empirical method with a strength test was used by the California Highway Department in 1929 in which the thickness of pavements was related to California Bearing Ratio, defined as the penetration resistance of the sub grade soil relative to the standard crushed rock. The disadvantage of this method is that it can be applied only to given set of environmental, material and loading conditions. If the conditions are changed, the design is no longer valid and new method must develop through trial and error to be commensurate with the new conditions (Huang, 1993).

The mechanistic-empirical method of design is based on the mechanics of materials that relates an input, such as a wheel load, pavement response such as stress or strain. The response values are used to predict distress based on laboratory test and field performance data. The concepts of design pavement was based on vertical compression and horizontal tensile strain. The vertical compressive strain on the surface of subgrade was used to control permanent deformation based on fact that plastic strains are proportional to elastic strains in paving materials, and horizontal tensile strain at the bottom of asphalt layer was to minimize fatigue cracking. The advantages of this method are improvement in the realibility of a design, the ability to predict the types of distress, and feasibility to extrapolate from limited field and laboratory data (Huang, 1993).

1.4 Problem of Statement

The problem statement for the thesis are as follows:

- i) Manual pavement design by Jabatan Kerja Raya (JKR) 1995 is based on empirical method (ASSHTO – 1972).
- ii) Adaptation ASSHTO Design Guide 1972 to Malaysia conditions based on an assumption that all materials behave as linearity elastic anisotropic.
- iii) In the reality, the unbound material is non-linear.

1.5 Objective of The Research

The objective of the study, are as follows:

- i) To determine the non-linearity characteristic of the unbound granular material as per JKR specification.
- ii) To determine the effect of a non-linearity of unbound granular material on the road performance.

1.6 Scope of Works

The scopes of work for the thesis are as follows:

- i) To review the literature on the unbound material characteristics and its effects on the road pavement performance, and to determine the characteristic of unbound material as per JKR specification.
- ii) To analyse effect of material non-linearity on the response of the typical pavement under standard axial load using available computer program.
- iii) To predict the performance of pavement based on the pavement structural responses.

CHAPTER II

LITERATURE REVIEW

2.1 Introduction

Pavement design evolved from the 1930's, with early methods solely based on empirical relationships. From 1950 onwards the increase in road transportation led to development of more sophisticated methods, initially for flexible pavements only based on solid relationships between theory and field observations and with pavements incorporating cement bound and similar stabilized materials.

Design of flexible asphalt pavements design based on primarily upon a theoretically related analysis involving some empirical modifications. Flexible pavements were classified by a pavement structure having a relatively thin asphalt-wearing course with layers of granular base and subbase being used to protect the subgrade from being over stressed. This type of pavement design was primarily based upon empiricism or experience, with theory playing only a subordinate role in the procedure.

2.2 The Principles of Pavement Design

Before designing a pavement, it is essential to understand the process which influence the behaviour of pavement under the action of time and traffic. These processes are rather different for flexible and rigid pavement and considered separately below.

2.2.1 Flexible Pavements

As soon as traffic begins to flow over a flexible pavement, permanent deformation will start to develop in the area of the wheel tracks followed by the commercial vehicles. This permanent deformation in a well-designed pavement is evenly distributed between the asphalted materials, the unbound base and sub base, and the sub grade. In bituminous materials, it may arise from additional compaction under traffic and from sideways displacement. In unbound materials and sub grade it will be due to traffic compaction, and only in very under designed pavements will shear in the sub grade be involved (Croney, 1998).

Wheel loads subject all pavement layers to vertical compressive stress. The wearing course, the binder course, and any bituminous base material will also be subject to tensile stress as the wheel load passes. The magnitude of this tensile stress in each layer will be determined by the effective modulus of elasticity of the layer and will be greater at the bottom of the layer. Lower bituminous layers will be subject to smaller tensile stress. Unbound granular materials used in bases and sub bases cannot accept significant tensile stress, and the structure of such layers will relax under load, so reducing the effective elastic modulus of the materials (Croney, 1998).

Structural failure will generally be initiated by fatigue cracking in the wearing course, followed by similar cracking in the binder course and any other bituminous layers.

2.2.2 Rigid Pavements

Rigid pavement or concrete pavements are not susceptible to surface deformation under traffic, and the normal process of structural deterioration is indicated by cracking. Wheel loads give rise to tensile stress in the underside of the slab, which in an under designed pavement give rise to fatigue cracking. Both the compressive and flexural strength of concrete increase considerably with age, and this process continues significantly up to a life of 10 years. The increase in flexural

strength will of course increase the tensile stress at the underside of the slab generated by a wheel load (Croney, 1998).

2.3 Granular Material as Base Course

In both flexible and rigid pavement, poor performance of unbound granular material contributes to reduce life and costly maintenance. The gradation of particle size distribution, density and moisture content of the material are factors that significantly influence the response of a granular material. These factors were accounted for in the preparation and selection of the sample for testing. They are not directly in the constitutive equation. Under the foregoing stated assumption that dominant aspect of the response of granular material is its non-linear character. The stress-strain character of the granular as expressed by the tangent modulus could be expressed as a function of the octahedral normal and shear stress (Nair et. al, 1973).

A base course is defined as the layer of material that lies immediately below the wearing surface of a pavement, and the sub base is a layer of material between the base and sub grade. Sometimes the material under a rigid pavement is called a subbase. Base courses may be constructed of stone fragments, slag, soil-aggregate mixtures and cement-treated granular materials. The function of the base course varies according to type of pavement. Base courses are used under rigid pavements and flexible pavement. For rigid pavement base course was used to prevention of pumping and prevention of volume change of the sub grade, to provide drainage and structure layer deformation. For flexible pavement base courses was used as base and sub bases to increase the load-supporting capacity of the pavement by providing added stiffness and resistance to fatigue as well as building up relatively thick layers to distribute the load through a finite thickness of pavement. This is the prime requirement of the base course and although to provide drainage when necessary (Yoder et. al, 1975).